

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 :

B29C 55/26, 65/20 // 53/40, 55/12, 55/30

A1

(11) International Publication Number:

WO 98/09796

(43) International Publication Date:

12 March 1998 (12.03.98)

(21) International Application Number:

PCT/NL96/00345

(22) International Filing Date:

2 September 1996 (02.09.96)

(71) Applicant (for all designated States except US): KONINKLIJKE EMBALLAGE INDUSTRIE VAN LEER N.V. [NL/NL]; P.O. Box 25, NL-1180 AA Amstelveen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): KEIMPEMA, Gerrit, Jan [NL/NL]; Schermerhornlanen 21, NL-3445 ET Woerden (NL). SHEFFORD, Roger, Alan [GB/NL]; De Hooghkamer 39, NL-2253 JV Voorschoten (NL).


(74) Agent: DE BRUIJN, Leendert, C.; Nederlandsch Octrooibureau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).

(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published

With international search report.

(54) Title: CONTAINER OF STRETCHED PLASTIC MATERIAL, AND PROCESS FOR MAKING SUCH CONTAINER



(57) Abstract

A container comprises a tubular container body (5) at the upper and lower ends of which end pieces (6) are connected. At least said container body comprises stretched plastic material. Also, at least one of the end pieces (6) may comprise stretched plastic material. A process for making the container comprising the steps of: extruding a tube (3) through an annular die (13); stretching the tube (3) in its axial and/or circumferential direction; cutting the tube in lengths so as to obtain a container body (5); connecting an end piece (6) to at least one end of each container body.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Container of stretched plastic material, and process for making such container.

The invention is related to the field of containers, for instance
5 semi bulk drums or containers e.g. in the range of 15 to 300 litres.
Such drums can be made of various materials, such as metal, glass or
plastics. Plastics have many advantages over competing materials, for
example low weight, transparency or translucency for viewing the
contents; they are suitable for packaging a wide range of products.
10 Moreover, plastics offer a much greater degree of freedom in shaping
the container which leads to more attractive designs and more convenience
for the consumer.

Plastics materials are very ductile, which means that the risk of
accidental breakage is decreased and the security of the contents is
15 increased. Minor denting of the drum recovers immediately, unlike
metal containers.

Plastics however have the disadvantage of a relatively low rigidity.
This means that the wall thickness of a plastic container or
drum is always much greater than the wall thickness of an equivalent
20 metal one. This increases the cost of a plastic container, not only
due to the greater amount of raw material required but also due to the
energy which is necessary for the conversion thereof.

Moreover, the size of such container is increased which leads to
a reduction of the number of containers which can be transported or
25 stored in a given vehicle or space. As a result the overall cost of
packaging is increased, and also the environmental impact.

These problems are furthermore of particular importance with
respect to the stacking capability of the drums. For instance, 200
litre steel drums can be stacked up to 5 metres high. Equivalent drums
30 from high density polyethylene can be stacked up to 3 metres high in
spite of a three times greater wall thickness.

Finally, many plastics absorb liquids and vapours, which reduces
their strength further. For example, HDPE will absorb hydrocarbon
solvents.

35 The object of the invention is to provide a container with an
increased rigidity, strength and impact resistance. Thereby a greater
stackability or a lower weight could be obtained, which could make the
plastic drums more equivalent to their steel counterparts.

Also a reduced absorption by the drum wall of components of the contents of the drum (such as hydrocarbons) is desired, to prevent a further reduction of the useful properties of the drum. Moreover, there should be a reduced permeability of the wall of the drum to
5 gases as well as components of the contents of the drum. These objects are achieved in that at least the container body comprises stretched plastic material.

The stretched material of the container body has a higher stiffness and strength than the corresponding non-stretched material.
10 Thereby, the resistance of the container body against external loads and buckling is increased appreciably, resulting in better stackability.

Also, the end pieces may consist of stretched material.

Preferably, the plastic is stretched into two mutually
15 perpendicular directions; for instance, the container body may consist of a length of biaxially stretched tubular material.

The invention is also related to manufacturing of an improved container. According to a first possibility, such process comprises the steps of:

- 20 -extruding a tube through an annular die;
- stretching the tube in its axial and/or circumferential direction;
- cutting the tube in lengths so as to obtain a container body;
- connecting an end piece to at least one end of each container
25 body.

Making containers from a continuously extruded tube with moulded ends per se is known from GB-A-1535287. Furthermore, various methods have been tried of improving the rigidity of the extruded tube. As an example, a closed cell foam has been used for the container walls.
30 Thereby the stiffness for a given weight is increased, but the wall thickness needs to be greater. Also, the impact strength is reduced considerably.

Furthermore, combinations of ribs and corrugations have been used, but their effects appeared to be only marginal.

35 By means of the process according to the invention, a container is obtained which has a thin-walled body with an excellent rigidity and strength. Both features are obtained by biaxially stretching the tube from which the body is made.

Manufacturing a bottle from an extruded stretched tube, by cutting said tube in appropriate lengths per se is known from EP-A-52490. This known process is however not suitable for manufacturing containers such as drums. In said known process, first of all a length
5 is cut from a piece of tubular material, and subsequently said length is stretched. The disadvantage here is that such process is not continuous but takes place in a batch-wise manner. Thereby, end-effects are generated in the lengths of tubular material, which makes this batch-wise process difficult to control.

10 In particular in processing larger diameter tubes, continuous stretching of the tubular material is preferred; it offers a faster process with a uniform quality and reduced failure rate.

Good results are obtained in case the container body is stretched up to 4 times in the radial direction, and the container body is
15 stretched 2-10 times in the axial direction.

Although the process described before is related to extruding a tube, the invention is not limited to such manufacturing method. For instance, according to a second possibility, the process could also comprise the following steps:

- 20
- stretching a plate of plastic material,
 - connecting two opposing edges of the stretched plate so as to form a tubular body,
 - connecting an end piece to at least one end of the tubular body.

25 The processes for connecting the end(s) according to the invention can be carried out in various ways. It may comprise the steps of:

-heating the surfaces of each end piece and the corresponding container body end by a heating device until the material of said
30 surfaces is molten;

- removing the heating device;
- pressing each end piece and the container body against one another until the material has solidified.

Alternatively, the process for connecting the end(s) to the tube
35 according to the invention may comprise the steps of:

- forcing at least one end of the container body over a conically shaped mandrel so as to form a conically shaped weldable surface;

-providing an end piece for each container body end having a correspondingly, conically shaped weldable surface;

-melting the material of the weldable surfaces;

-pressing each end piece into and against the conically shaped
5 end of the container body until the material has solidified.

Welding the ends to the container body is also possible in several ways, for instance by means of an ultrasonic device, by an infra-red device, or by a vibration device.

The end piece may also be connected to the container body by
10 means of glueing.

For manufacturing a drum with a barrel-shape, the process may additionally comprise the step of heating the container body at least one of its ends for shrinking the plastic material so as to form an end with a converging shape.

15 Furthermore, it is observed that in the process of manufacturing a container from an extruded tube, proper control mechanisms should be applied for cooling the inside and the outside of the extruded tube, so as to obtain a regular stress distribution over the wall thickness. This can for instance be done according to the process described in
20 EP-A-209933. A uniform temperature distribution is necessary in order to enable the stretching process to be carried out in a proper way.

The invention will be explained further with reference to the figures, related to only one of the possible embodiments and methods of manufacturing.

25 Figure 1 shows a schematic view of biaxially stretching a tube.

Figure 2a and b show a first method of welding an end plate to a drum body by means of a hot plate.

Figure 3 shows a second method for welding an end plate to a drum body.

30 A tube of stretchable thermoplastic material such as high density polyethylene (HDPE) is extruded through an annular die 13 and is pulled through a cooling bath 14 by a pulling device 15 such as a set of caterpillars which are situated at regular intervals around the tubes. It is subsequently reheated by a reheater 12 and pulled over a
35 mandrel 1. The cooling and heating sections have to be adjusted so that the HDPE is in the temperature range of 100°C-130°C when it is pulled over the mandrel. The mandrel is held in place by means of a pulling rod 2, which is fixed to the extrusion die 13.

The tube 4 is pulled over the mandrel 1 by means of pulling device 16 which may also be a set of caterpillars which are situated at regular intervals around the tube. In this pulling process the tube is stretched in the axial direction. Radial stretching also occurs as the tube 3 is pulled over the mandrel 1.

By changing the cross sectional shape of the mandrel (e.g. square or rectangular) a similarly shaped tube can be made.

The biaxially stretched tube 4 thus obtained is cut into pieces of appropriate size 5 by cutting means (not shown).

10 The pieces 5 thus obtained are to form the drum body of a drum. Figures 2a and 2b show a drum body 5 in question, at one end of which an end piece 6 is situated. By means of a hot plate 7, the facing surfaces of drum body 5 and end piece 6 are heated, such that they can be fused together by pressing them onto each other.

15 In the embodiment of figures 3a and 3b the end of the drum body 5 is forced over a conical heating ring 8, whereby both a conical end section 9 is obtained, and the inner surface of this end section 9 is molten. Furthermore, the end moulding 10, in particular the outer surface 11 thereof, is heated by means of a heating ring 12 until said surface 11 melts.

20 Subsequently, heating rings 8 and 12 are removed, and the end moulding 10 is pressed into the conically widened end section 9 of drum body 5. Thereby, a solid bond as shown in figure 3b is obtained.

25 Although in the embodiments described the end pieces are welded to the container body, other methods may be applied as well, such as glueing.

C l a i m s

1. Container, comprising a tubular container body at the upper and lower ends of which end pieces are connected, characterized in
5 that at least the container body comprises stretched plastic material.
2. Container according to claim 1, wherein at least one of the end pieces comprises stretched plastic material.
- 10 3. Container according to claim 1 or 2, wherein the plastic material is stretched into two mutually perpendicular directions.
4. Container according to claim 3, wherein the container body is stretched up to 4 times in the radial direction.
- 15 5. Container according to claim 3 or 4, wherein the container body is stretched 2-10 times in the axial direction.
6. Container according to claim 1, 2, 3, 4, or 5, wherein the
20 container body consists of a length of biaxially stretched, tubular material.
7. Container to claims 1 to 6, wherein one or both of the ends are of a different colour to the body.
- 25 8. Container according to claims 1 to 6, wherein one or both of the ends are of a different material to the body.
9. Process for making a container according to any of claims 1-8
30 comprising the steps of:
- extruding a tube through an annular die;
 - stretching the tube in its axial and/or circumferential direction;
 - cutting the tube in lengths so as to obtain a container body;
 - 35 -connecting an end piece to at least one end of each container body.

10. Process according to claim 9, whereby the tube is cooled as it is extruded and reheated to the correct temperature before stretching.

5 11. Process according claim 10, whereby the cooling is applied to both the inside as well as the outside of the tube.

12. Process for making a container according to any of claims 1-8, comprising the steps of:

- 10
- stretching a plate of plastic material,
 - connecting two opposing edges of the stretched plate so as to form a tubular body,
 - connecting an end piece to at least one end of the tubular body.

15

13. Process according to any of claims 9-12, whereby an end piece is connected to both ends of the container body.

20 14. Process according to any of claims 9-14 comprising the steps of:

-heating the surfaces of each end piece and the corresponding container body end by a heating device until the material of said surfaces is molten;

-removing the heating device;

25 -pressing each end piece and the container body against one another until the material has solidified.

15. Process according to any of the claims 9-14, comprising the steps of:

30 -forcing at least on end of the container body over a conically shaped mandrel so as to form a conically shaped weldable surface;

-providing an end piece for each container body end having a correspondingly, conically shaped weldable surface;

-melting the material of the welding surfaces;

35 -pressing each end piece into and against the conically shaped end of the container body until the material has solidified.

16. Process according to claim 14 or 15, whereby each end is welded to the container body by means of a hot plate.

17. Process according to claim 14 or 15, whereby each end is
5 welded to the container body by means of an ultrasonic device.

18. Process according to claim 14 or 15, whereby each end is welded to the container body by an infra-red device.

10 19. Process according to claim 14 or 15, whereby each end is welded to the container body by means of a vibration device.


20. Process according to any of claims 9-12, whereby each end piece is connected to the container body by glueing.





15

21. Process according to any of claims 9-20, comprising the step of heating the container body at at least one of its ends for shrinking the plastic material so as to form an end with a converging shape.

20

fig -1





INTERNATIONAL SEARCH REPORT

International Application No.

PCT/NL 96/00345

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B29C55/26 B29C65/20 //B29C53/40, B29C55/12, B29C55/30

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C B65D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 447 199 A (REED LEONARD W ET AL) 8 May 1984 cited in the application see column 3, line 60 - column 6, line 56; claim 14; figures 1-6 ---	1-11
X	US 4 809 876 A (TOMASWICK KATHLEEN M ET AL) 7 March 1989 see column 3, line 29 - line 65; figures ---	1-8
X	GB 2 156 268 A (VERCON INC) 9 October 1985 see page 2, line 31 - line 38 see page 4, line 5 - line 65; figures 4-6, 14-17 --- -/-	1-8, 12-21

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

& document member of the same patent family

Date of the actual completion of the international search

20 May 1997

Date of mailing of the international search report

19.06.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patenlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Topalidis, A

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/NL 96/00 45

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 649 962 A (VINOKUR ISAAC) 17 March 1987 see abstract see column 3, line 42 - column 4, line 9; figures	1,12
A	--- US 3 967 991 A (SHIMANO IKUYA ET AL) 6 July 1976 see column 4, line 9 - line 18 see column 7, line 26 - column 8, line 58; figures 5-7	12-21
A	--- WO 95 25628 A (WAVIN BV ;PRENGER JAN HENDRIK (NL); SCHUURMAN JOHAN (NL); VISSCHER) 28 September 1995 see abstract; figure	9-11
A	--- EP 0 371 769 A (NAT RES DEV) 6 June 1990 see page 5, line 1 - line 7; figure	9-11
A	--- EP 0 689 926 A (RHONE POULENC FILMS) 3 January 1996 see abstract see page 4, line 35 - line 54 -----	2

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 96/00345

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4447199 A	08-05-84	GB 2089276 A	23-06-82
		AU 559758 B	19-03-87
		AU 3350884 A	17-01-85
		AU 540844 B	06-12-84
		AU 7744981 A	27-05-82
		CA 1170806 A	17-07-84
		CA 1211390 C	16-09-86
		EP 0052490 A	26-05-82
		EP 0150866 A	07-08-85
		JP 1590687 C	30-11-90
		JP 2014886 B	10-04-90
		JP 57115324 A	17-07-82
		KE 3524 A	24-05-85
		US 4547416 A	15-10-85
		US 4735538 A	05-04-88
US 4809876 A	07-03-89	NONE	
GB 2156268 A	09-10-85	AU 3866985 A	03-10-85
		BE 902021 A	26-09-85
		DE 3510956 A	07-11-85
		FR 2561575 A	27-09-85
		GB 2156265 A	09-10-85
		JP 60224533 A	08-11-85
		SE 8501423 A	27-09-85
		AU 4099185 A	24-10-85
		JP 60232940 A	19-11-85
US 4649962 A	17-03-87	AU 577124 B	15-09-88
		AU 4397785 A	02-01-86
		BR 8503035 A	11-03-86
		CA 1245096 A	22-11-88
		EP 0166226 A	02-01-86
		JP 1876912 C	07-10-94
		JP 6000379 B	05-01-94
		JP 61083024 A	26-04-86
US 3967991 A	06-07-76	JP 975063 C	19-10-79
		JP 50063077 A	29-05-75
		JP 53004556 B	18-02-78

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 96/00345

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3967991 A		JP 945703 C	30-03-79
		JP 49081480 A	06-08-74
		JP 52038593 B	29-09-77
		AU 452152 B	29-08-74
		AU 6323873 A	29-08-74
		CA 1041261 A	31-10-78
		CH 573300 A	15-03-76
		DE 2361038 A	27-06-74
		FR 2209657 A	05-07-74
		GB 1435217 A	12-05-76
		NL 7316710 A,B,	11-06-74
WO 9525628 A	28-09-95	NL 9400452 A	01-11-95
		AU 1962195 A	09-10-95
		CA 2185701 A	28-09-95
		EP 0751862 A	08-01-97
		FI 963738 A	20-09-96
		PL 316237 A	06-01-97
EP 0371769 A	06-06-90	AT 128667 T	15-10-95
		AU 636586 B	06-05-93
		AU 4561489 A	07-06-90
		CA 2004103 A	31-05-90
		DE 68924467 D	09-11-95
		DE 68924467 T	09-05-96
		GB 2225551 A,B	06-06-90
		JP 2258323 A	19-10-90
EP 0689926 A	03-01-96	FR 2721935 A	05-01-96
		BR 9502952 A	12-03-96
		CA 2153088 A	02-01-96
		CN 1133226 A	16-10-96
		CZ 9501721 A	17-01-96
		FI 953254 A	02-01-96
		HU 73290 A	29-07-96
		NO 952630 A	02-01-96
		PL 309419 A	08-01-96
		SK 85195 A	10-01-96
		ZA 9504880 A	31-01-96